



TECHNICAL DATA SHEET – HPC 59 NU-STEEL QD

PRIMER /UNDERCOAT

DESCRIPTION:

Nu-Steel QD Primer / Undercoat is a high performance phosphate primer and undercoat.

ADVANTAGES:

Provides first class adhesion to properly prepared surfaces. Being quick drying this system is ideally suited for application to steelwork requiring a fast return to public use.

USES:

First coat of the Nu-Steel QD System.

COLOUR RANGE:

Available in Grey and Red Oxide.

PACK SIZE:

Single component product, supplied in 5 litre units.

VOLUME SOLIDS:

55%

COVERAGE RATE:

8-10 m² / Litre

DRYING TIME:

Touch: 15-20 Minutes
Overcoat: 1-2 Hours.

PREPARATION:

Ensure surfaces to be treated are clean, free from contamination and dry. Previously coated surfaces should be abraded

APPLICATION:

Airless spray. May be applied by brush/roller on small section steel. Should not be applied at temperatures below 5°C or when the relative humidity exceeds 85%.

EQUIPMENT CARE:

All equipment should be cleaned with T1 Thinners

STORAGE:

Store away from direct sunlight and sources of heat. Protect from frost.

SHELF LIFE:

12 months (in original sealed container).

HEALTH & SAFETY:

Refer to MSDS